



SEAL KING

🌐 www.sealking.ca
✉ info@sealking.ca
☎ 833-933-7325

Concrete Cure and Seal - Technical Data Sheet



Description

SEAL KING's Cure and Seal is specially formulated from acrylic polymers and fast drying solvents to cure and seal fresh concrete, stamped or otherwise. By regulating water evaporation Seal King's Cure and Seal creates a stronger concrete while still giving the benefits of a regular sealer. This complies with ASTM C-1315 and C-309 for water retention and complies with ASTM C-156 for drying time.

Application Instructions

- Surface must be clean and free of standing water.
- Remove any oil, dirt or other contaminants.
- Apply with a hand held pump sprayer or roller.
- Allow 2.5 hours for touch dry, 24 hours for full cure

Available Sizes

18.9L / 5 Gallons
3.78L / 1 Gallon

Available Finishes

High Gloss

Coverage

Sealant will cover approximately 160 sq. ft./1gal.

Caution

- Do not use indoors.
- This product contains flammable solvents, keep away from open flames and heat. Do not smoke when applying this product.
- Avoid skin and eye contact, if contact occurs wash thoroughly with cold water.
- Avoid breathing vapors. Use adequate ventilation.
- Keep the container closed when not in use.
- Store in a cool dry place. Protect from freezing.
- Keep away from children.

PLEASE NOTE

- Apply only when the concrete surface is above 4°C(40°F).
- Keep vapors away from foodstuff.
- Will not resist other solvents and gasoline.
- Use Seal King's Grease Release to clean equipment.
- V.O.C Compliant

Warranty

Our ISO 9001 audit procedures confirm strict quality control of our products in manufacture within approved tolerances. Our products are warranted to be free of defects in material or manufacture. If a product does not conform to this warranty, Seal King's sole obligation under this warranty shall be, at its option, to credit the Purchaser's account or to supply replacement material. All information and recommendations given in this document are accurate on the date of publication.

Please consult the Safety Data Sheet for more Hazard Information.